

Heat Transfer Type	Temp	Pressure	Time
Smooth	305° F / 150° C	Medium	10 - 15 sec
Flocked	320° F / 160° C	Medium	15 - 20 sec
Glitter	320° F / 160° C	Firm	10 - 15 sec
Metallic	305° F / 150° C	Medium-Firm	15 - 20 sec
Reflective	320° F / 160° C	Medium-Firm	15 - 20 sec
Fabric	320° F / 160° C	Firm	15 - 20 sec
Iridescent	320° F / 160° C	Medium-Firm	15 - 20 sec
Glow-in-the-Dark	345° F / 175° C	Firm	20 - 25 sec
Printable for Light Fabrics	345° F / 175° C	Firm	15 - 20 sec
Printable for Dark Fabrics	345° F / 175° C	Firm	15 - 20 sec
Printable Fabric Texture	345° F / 175° C	Firm	15 - 20 sec

Heat Transfer Type	Teflon Sheet	Peel Type
Smooth	Yes	Hot
Flocked	Yes	Cold
Glitter	Yes	Hot or Cold
Metallic	Yes	Cold
Reflective	Yes	Cold
Fabric	No	Hot or Cold
Iridescent	Yes	Cold
Glow-in-the-Dark	No	Hot
Printable for Light Fabrics	Yes	NA
Printable for Dark Fabrics	Yes	NA
Printable Fabric Texture	No	NA